



LIMEROCK BEARING RATIO TEST REPORT

Moisture Content Versus Density



Moisture Content Versus LBR Value



PROJECT INFORMATION

GEC Project No:	3980C	Project Name:	Buck Hammock Paver Base
-----------------	-------	---------------	-------------------------

SAMPLE INFORMATION

Sample ID:	LBR	Sample Location:	Buck Hammock
Date Tested:	2-22-21	Tested By:	RSR
Soil Description:	Shell Base for Pavers		

MODIFIED PROCTOR TEST RESULTS

Optimum Moisture (%):	9.3	Maximum Dry Density (pcf):	128.5
-----------------------	-----	----------------------------	-------

LBR TEST RESULTS

	At Opt. Moisture	At -2% of Opt. Moisture	At +2% of Opt. Moisture
LBR Value:	121	N/A	N/A